

Intumescent fire protection coating

6000

Description:

Corrofire 6000 is an intumescent fire protection coating with an excellent thermal efficiency in today's market. From a design standpoint, it is now possible to achieve 60 Minutes fire protection to steel structural with only 1.5 mm. thickness.

Recommended use:

As an intermediate and topcoat on primed steel to protect that from fire.

Service temperature:

Dry: Maximum 50°C

PHYSICAL CONSTANTS:

Colors/Shade:	White
Finish:	Flat
Volume Solid:	50%
Theoretical spreading rate:	1.67 m ² /liter – DFT: 300 µm
Flash point:	22oC
Specific gravity:	App. 1.3 kg/liter
Surface dry:	Max. 2 hours at 20°C (ISO 1517)
Dry to touch:	Max. 4 hours at 20°C
Fully cured:	15 days
Shelf life:	1 Year (25°C) from time of production. Depending on storage condition, mechanical stirring may be necessary before usage.

APPLICATION DETAILS:

Application method:	Airless sprays	Brush (touch-up)
Thinner (max. vol.)	6001 (5%)	6001 (5%)
Nozzle orifice:	0.023"	
Nozzle pressure:	260 bar / 3770 Psi	
	(Airless spray data are indicative and subject to adjustment)	
Cleaning of tools:	6003	
Indicated film thickness, dry:	1000 microns (in several coats)	
Indicated film thickness, wet:	2000 microns (in several coats)	
Recoat interval, min:	8 hours (20°C)	
Recoat interval, max:	None	
Issued:	June 2018	

TEL/FAX : +2 02 26392604

MOB : +2 01016042932

Email : info@corrocoategypt.com

Head Office: 17A- Abdel Wahab Khalifa St. - off Abdel Aziz Fahmy St. - Heliopolis, Cairo.

Factory : New Indust. Zone Bany Swaif Governorate.

www.corrocoategypt.com


CORROCOAT
EGYPT
home of engineering coating

intumescent fire protection coating

6000

SURFACE PREPARATION:

Remove oil and grease, etc. with suitable detergent. Remove salt and other contaminants by (high pressure) fresh water cleaning.

Abrasive blasting to Sa 2. SSPC-SP-10, with a sharp-edged surface profile corresponding to ISO Comparator, Medium (G) corresponding to Segment 2.

APPLICATION AND CURING CONDITIONS:

The surface must be completely clean and dry at the time of application. And its temperature must be above the dew point to avoid condensation. Minimum temperature for curing is 5°C.

At the freezing point and below, be aware of the risk of ice on the surface which will hinder the adhesion. High humidity and/or condensation during application and the following 16 hours (20°C) may adversely affect the film formation.

In confined spaces provide adequate ventilation during application and drying.

PRECEDING COAT: Corrozinc phosphate.

REMARKS:

Film thicknesses:

May be specified in another film thickness than indicated depending on purpose and area of use. This will alter spreading rate and may influence drying time and recoating interval.

Normal range is 300 microns. For more than 1 hours fire protection more coats should be applied.

Thinning:

The type and amount of thinner depends on application conditions, application method, temperature, ventilation, and substrate. Thinner 6001 is recommended in general.

Recoating:

A completely clean surface is mandatory to ensure inter coat adhesion, especially at long recoating intervals. Any dirt, oil, and grease have to be removed, e.g. with suitable detergent. Salts to be removed by fresh water hosing. To check an adequate quality of the surface cleaning a test patch is recommended before actual recoating.

SAFETY:

Handle with care. Before and during use, observe all safety labels on packing and paint containers, consult Corrocoat material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance swallowed.

Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant.

Always take precautions against the risks of fire and explosions.

Issued: June 2018

TEL/FAX : +2 02 26392604

MOB : +2 01016042932

Email : info@corrocoategypt.com

Head Office: 17A- Abdel Wahab Khalifa St. - off Abdel Aziz Fahmy St. - Heliopolis, Cairo.

Factory : New Indust. Zone Bany Swaif Governorate.

www.corrocoategypt.com


CORROCOAT
EGYPT
home of engineering coating